

# ACRYCLEAR HS EXTRA FAST MATT ZA 30

\*



**2004/42/IIB  
e(840)600**

ACRYCLEAR HS EXTRA FAST MATT ZA 30 is a 2K matt extrafast air drying clearcoat, (AIR DRY tecnology) ANTI-SCRATCH, compliant with EC directive 2004/42/CE.

Thanks to its features it is suitable for:

- spot e large repair
- application both on mat solvent base and on water-soluble base
- very good resistance to light and to weather
- no lens effect
- energy saving (NO BAKING)
- higher productivity

## application

### mixing ratio

2 : 1 by volume – 50% by weight



ACRYDUR ST HS QA 2300

large repair

ACRYDUR FAST HS QA 2310

spot repair

### pot – life

2 hours at 25°C

## application



thinness

ready for use

application viscosity

16 – 14 seconds DIN4



spray nozzle

1,3 – 1,4 mm

spraying pressure

2 – 3 bar



number of coats

2

film thickness

35 – 45 micron



LET THE SURFACE BECOME MATT AFTER EACH LAYER'S APPLICATION

## drying

air drying at 20°C

QA 2300 ST HS

QA 2310 FAST HS



dust free

10 minutes

5 minutes

dry for handling

50 minutes

30 minutes

REMARKS To get best results, it is important to select the correct hardener on the base of structure size and on application temperature. With mixing ratio 2:1 , the product is ready for use and no additional thinning is necessary.

\*.PICTUREGRAPH LEGENDA

**2004/42** Reference to the CE law

**IIBe** Annex,Table and Category of product

**(840)** Limit value of VOC with reference to the category of product

**600** Maximum VOC content of the product ready for the use

160630r

*The information given in this technical data sheet is based on present scientific and technical knowledge and thus do not exempt the customer to test the suitability of our products for the use and for the intended purposes.*

**EP vernici s.r.l.**

Via Roma,12 I-48027 Solarolo (RA) tel.+39 0546 53322 fax +39 0546 53323 email: laboratorio@epvernici.it [www.epvernici.it](http://www.epvernici.it)

