

ACRYCLEAR ZA 10



ACRYCLEAR ZA 10 is a 2K ANTI-SCRATCH HS acrylic clear. It is compliant to EC directive 2004/42/EC.

Thanks to its features it is suitable for:

- complete or partial car painting
- application both on mat solvent base coat and on water- based base coat without absorption
- excellent glossy
- easy application
- no lins effect
- very good resistance to light and to weathering

application					
mixing ratio		2 : 1 by volume – 50% by weight			
[]	use temperatures	< 18°C	ACRYDUR FAST QA 2007		
\square		18 – 27°C	ACRYDUR ST QA 2006/QA 2044		
		> 27°C	ACRYDUR SLOW QA 2008		
pot - life		2 – 3 hours			
thinners		ACRYTHINNER X 16			
		ACRYTHINNER FAST X 22			
		ACRYTHINNER SLOW X 33			

application							
	thinning	5 %					
\mathbb{Z}^{s}	application viscosity	16 – 17 seconds DIN4					
	spray nozzle	1,3 – 1,4 mm					
₹ T	application pressure	2 – 3 bar					
	number of coats	2					
	film thickness	40 – 50 dry micron					
drying							
hardeners		ST QA 2006 ST QA 2044	FAST QA 2007	SLOW QA 2008			
air drying	at 25°C						
	dust free	15 – 20 minutes	10 minutes	20 minutes			
()	dry for handling	not available	4 – 6 hrs	not available			
	depth	12 hrs	6 – 8 hrs				
baking							
<u>)</u> ,),)	flash off time	10 minutes		10 minutes			
	drying	30 minutes 60°C		40 minutes 60°C			
infra-red drying short waves							
<u>}t}t</u>	flash off time	5 – 10 minutes					
	drying	5 min at 50°C, after 8 min at 90°C		5 min at 50°C, after 8 min at 90°C			

*.PICTUREGRAPH LEGENDA				
2004/42	Reference to the EC law			
IIBe	Annex, Table and Category of product			
(840)	Limit value of VOC with reference to the category of product			
585	Maximum VOC content of the product ready for the use			

220131

The information given in this technical data sheet is based on present scientific and technical knowledge and thus do not exempt the customer to test the suitability of our products for the use and for the intended purposes.