

CARTOP 2K CT

*



**2004/42/IIB
d(420)420**

CARTOP 2K CT is a high performing 2K acrylic topcoat that is compliant with 2004/42/EC directive, 418 g/l VOC, for car refinish use.

- very good fullness and spreading properties
- very good resistance to atmospherical and chemical agents
- high coverage
- it can be mixed with different hardeners and thinners, adapting to different application needs

application

mixing ratio

2 : 1 by volume – 40% by weight

ACRYDUR ST UHS QA 2070

ACRYDUR FAST UHS QA 2090

ACRYDUR SLOW UHS QA 2069



pot – life

2 hours abt. at 20°C

application – for usage 2 : 1



thinness with X 16

5%

application viscosity

18 – 20 seconds DIN4



spray nozzle

1,4 mm

spraying pressure

3 – 4 bar



number of coats

1,5

film thickness

50 – 60 micron

drying

air drying at 20°C



dust free

25 – 30 minutes

dry for handling

6 – 8 hours

depth

12 – 18 ore

baking



flash off time

15 – 20 minutes



drying

25 – 30 minutes at 60°C on the piece

*.PICTUREGRAPH LEGENDA

2004/42 Reference to the CE law

IIBd Annex, Table and Category of product

(420) Limit value of VOC with reference to the category of product

420 Maximum VOC content of the product ready for the use

180327

The information given in this technical data sheet is based on present scientific and technical knowledge and thus do not exempt the customer to test the suitability of our products for the use and for the intended purposes.

EP vernici s.r.l.

Via Roma,12 I-48027 Solarolo (RA) tel.+39 0546 53322 fax +39 0546 53323 email: laboratorio@epvernici.it www.epvernici.it

