


MASTIC EMN 15

*



**2004/42/IIB
b(250)250**

MASTIC EMN 15 is a polyester putty used for car refinish field, in compliance with 2004/42/CE law.

Thanks to its features it is particularly suitable for:

- general supports as sanded steel
- good sanding and drying properties
- good infrared drying

substrate pre-treatment



sand and degrease carefully

application

method of application



by spatula

mixing ratio



1 – 3 %

pot – life

3 – 5 minutes at 20°C

drying

air drying at 20°C



20 – 30 minutes

sanding



AS BODY FILLER

first sanding: dry with P80 – P120

final sanding: dry with P180 – P240

FOR FINE PUTTY

first sanding: dry with P120 – P180

final sanding: dry with P240 – P280



* PICTUREGRAPH LEGENDA

2004/42 Reference to the CE law

IIBb Annex, Table and Category of product

(250) Limit value of VOC with reference to the category of product

250 Maximum VOC content of the product ready for the use

150315

The information given in this technical data sheet is based on present scientific and technical knowledge and thus do not exempt the customer to test the suitability of our products for the use and for the intended purposes.

EP vernici s.r.l.

Via Roma,12 I-48027 Solarolo (RA) tel.+39 0546 53322 fax +39 0546 53323 email: laboratorio@epvernici.it www.epvernici.it

