

## UNIBASE BOZ

UNIBASE BOZ is a solvent based base coat that is suitable for double coat finishing in metallic dyes. To get a glossy, outdoor resistant result, we highly recommend to use our ACRYCLEAR clear coats.

application		
ratio mix binder with	VBOZ/BP55 all magnum	65/35
EUROMIX	VBOZ/BP65 all medium	70/30
	VBOZ/BP75 all fine VBOZ/BP85 all. extrafine	80/20
thinner 80 – 100 % with	ACRYTHINNER X 16	
	ACRYTHINNER FAST X 22	
	(application on small surfaces)	
	ACRYTHINNER SLOW X 33	
	(application on large surfaces)	

substrate pretreatment			
<u>F</u>	old and original paintworks, fillers, carefully cleaned and sanded - dry with sand paper P400 – P500 - moist with sand paper P800 – P1000		

hardener			
	7%	ACRYDUR ST HS QA 2150	
	5%	ACRYDUR ST UHS QA 2070	

application				
	application viscosity	16 – 18 seconds DIN4		
$\langle \rangle$	thinning	1:1		
	nozzle	1,3 mm		
T.	application pressure	3 – 4 bar		
	number of coats	2 - 3 (between the coats, flash off time of $5 - 15$ minutes)		
<u>}</u>	flash off time	15 – 30 minutes at 20°C according to the used thinner		

170217

The information given in this technical data sheet is based on present scientific and technical knowledge and thus do not exempt the customer to test the suitability of our products for the use and for the intended purposes.

