

ACRYCLEAR HS MATT ZA 09

*



**2004/42/IIB
e(840)550**

ACRYCLEAR HS MATT ZA 09 is a 2k satin elastic clear coat matt, in compliance with the 2004/42/CE law:

- very good performances against scratches due to automatic car wash, preserving gloss and long lasting.
- matt appearance
- extreme elasticity and grappling
- suitable for painting of plastic supports for example car bumpers and/or trims

application

mixing ratio 3 : 1 by volume – 35% by weight



ACRYDUR ST UHS QA 2070

ACRYDUR FAST UHS QA 2090

pot – life 1 – 2 hours

thinner 15 – 20% ACRYTHINNER X 16
ACRYTHINNER FAST X 22

application



thinness

conventional

20 %

application viscosity

16 – 17 seconds DIN4



spray nozzle

1,3 mm

spraying pressure

2 – 3 bar



number of coats

1,5

film thickness

40 micron

drying

air drying at 20°C

QA 2070 ST UHS

QA 2090 FAST UHS



dust free

15 – 20 minutes

10 minutes

dry for handling

3 – 4 hours

1 – 2 hours

depth

6 – 8 hours

6 – 8 hours

*.PICTUREGRAPH LEGENDA

2004/42 Reference to the CE law

IIBe Annex, Table and Category of product

(840) Limit value of VOC with reference to the category of product

550 Maximum VOC content of the product ready for the use

180718

The information given in this technical data sheet is based on present scientific and technical knowledge and thus do not exempt the customer to test the suitability of our products for the use and for the intended purposes.

EP vernici s.r.l.

Via Roma,12 I-48027 Solarolo (RA) tel.+39 0546 53322 fax +39 0546 53323 email: laboratorio@epvernici.it www.epvernici.it

