

CARTOP 2K CH

*



**2004/42/IIB
e(840)500
With QA UHS**

CARTOP 2K CH is a high performing 2K ANTI-SCRATCH acrylic topcoat that is compliant with 2004/42/EC directive, 500 g/l VOC, for car refinish use.

- very good fullness and spreading properties
- very good resistance to weathering and chemical agents
- high coverage, easy application and flow
- it can be mixed with different hardeners and thinners, adapting to different application needs

application

mixing ratio



pot – life

2 : 1 by volume – 40% by weight

ACRYDUR ST UHS QA 2070

ACRYDUR FAST UHS QA 2090

ACRYDUR SLOW UHS QA 2069

50% by weight

ACRYDUR ST QA 3500

ACRYDUR FAST QA 3600

ACRYDUR SLOW QA 3700

2 hours abt. at 20°C

application – for usage 2 : 1



thinness with X 16

5 – 10%

application viscosity

18 – 20 seconds DIN4



spray nozzle

1,4 mm

spraying pressure

3 – 4 bar



number of coats

1,5

film thickness

50 – 60 micron

drying

air drying at 20°C



dust free

25 – 30 minutes

dry for handling

6 – 8 hours

depth

14 – 16 ore

baking



flash off time

15 – 20 minutes



drying

30 minutes at 60°C on the piece

*.PICTUREGRAPH LEGENDA

2004/42 Reference to the CE law

IIBe Annex, Table and Category of product

(840) Limit value of VOC with reference to the category of product

500 Maximum VOC content of the product ready for the use

180917

The information given in this technical data sheet is based on present scientific and technical knowledge and thus do not exempt the customer to test the suitability of our products for the use and for the intended purposes.

EP vernici s.r.l.

Via Roma,12 I-48027 Solarolo (RA) tel.+39 0546 53322 fax +39 0546 53323 email: laboratorio@epvernici.it www.epvernici.it

