


FILLER 1K FU

*



**2004/42/IIB
c(540)540**

FILLER 1K FU is one-component nitro-acrylic filler:

The product is characterised by:

- fast drying time
- easy to apply
- excellent coverage
- very good sanding property

substrate pre-treatment



sand



clean accurately the surface, then apply ANTISIL X 29R

application



thinness

20 – 25 % with nitro thinner

application viscosity

25 – 30 seconds DIN4



spray nozzle

1,8 mm

spraying pressure

2 – 3 bar



number of coats

2 – 3

film thickness

70 – 80 micron

drying

air drying at 20°C



dust free

10 minutes

depth

30 – 40 minutes

dry for sanding

after 2 – 3 hours

sanding



sand with sand paper P320 – P400



wet hand sanding with sand paper P600 – P800

*PICTUREGRAPH LEGENDA

2004/42

Reference to the CE law

IIBc

Annex, Table and Category of product

(540)

Limit value of VOC with reference to the category of product

540

Maximum VOC content of the product ready for the use

150315

The information given in this technical data sheet is based on present scientific and technical knowledge and thus do not exempt the customer to test the suitability of our products for the use and for the intended purposes.

EP vernici s.r.l.

Via Roma,12 I-48027 Solarolo (RA) tel.+39 0546 53322 fax +39 0546 53323 email: laboratorio@epvernici.it www.epvernici.it

