


- product name : SMALTO VINILICO SEO

Product is compliant with directive 2004/42/EC	
	car refinish see note 1 2004/42 IIBe(840)640

pictogram legend	
2004/42	Reference to EC Directive
IIAj	Annex, Table and Sub-category of product
(500)	Limit value of VOC with reference to the product sub-category
500	Maximum VOC content in product ready for use

IT CAN BE PRODUCED IN TINTING SYSTEM

VSEO BINDER 85
BPN 15

- general features

Synthetic finishing coat based on vinyl copolymers with an excellent anti-corrosion power.
Excellent hiding power.
Perfect spray application.
Excellent adhesion on metal, aluminum and zinc plated sheets.
Extremely fast drying.
Good outdoor resistance.

- use

After pre-treatment with mechanical devices or sandblasting, this product is used as single protection coat on iron, zinc plated sheets, aluminum and light alloys.
It is not suitable to protect surfaces that are in contact with strong solvents.

- recommended cycles

Spray application of one or more coats on pre-treated structure, in compliance with overcoating times.
Recommended application as topcoat on FONDO ALFA PE primer, also wet on wet.

- application and thinning method

spray : 10 - 20% with X 2 (nitro)
airless : 5 - 10% with X 2 (nitro)

- technical and supply data

specific weight : min. : 1,340 g/l - max. : 1,450 g/l

note 1: 20% thinning with X2

solid content : by weight : min. 58,0 % - max. 63,0 %
by volume : min. 36,5 % - max. 37,5 %

film appearance : matt

colour : on demand

product type : One-component

dry film thickness : 35 - 40 microns

theoretical coverage : min. 9,2 m²/l - max. 11,5 m²/l

drying at 25°C :
dust free : 10 - 15 minutes
touch free : 15 - 20 minutes
depth : 40 - 50 minutes

overcoating time :
min : after 4 - 5 hours - max. : unlimited

shelf life : 24 months at + 5/35°C.