


- product name : SPARTITRAFFICO NON RIFRANGENTE B

Product is compliant with directive 2004/42/EC



building sector
see note 1
2004/42
IIAi(500)470

pictogram legend

2004/42 Reference to EC Directive
IIAj Annex, Table and Sub-category of product
(500) Limit value of VOC with reference to the product sub-category
500 Maximum VOC content in product ready for use

IT CAN BE PRODUCED IN TINTING SYSTEM

VB BINDER **85** **75** yellow and red organic pigments
BPN **15** **25**

note 1: 5 - 10% thinning with X2

- general features

Synthetic paint, dries quickly and has excellent covering properties.

solid content : by wgt = min. 72,0 % - max. 76,0 %
by vol. = min. 52,0 % - max. 56,0 %

film appearance : matt

colour : on demand

availability on stock: white color / B 92

product type : One-component

- use

Ideal for upkeep of road signs, applied by spraying or roller.

dry film thickness : 50 - 60 microns

theoretical coverage : min. 8.0 m²/l - max. 10.0 m²/l

drying at 25°C :

dust free : 10 - 15 minutes
touch free : 25 - 35 minutes
depth : 2 - 3 hours
polymerised : about 7 days

- recommended cycles

Directly on perfectly dry asphalt.

overcoating time :

min: 2 - 3 hours - **max.:** unlimited

shelf life : 24 months at + 5/35°C.

- application and thinning method

roller : 10 - 15% with X 2 (nitro) or X 100
spray : 10 - 20% with X 2 (nitro)

- technical and supply data

specific weight min. 1,540 g/l - **max.** 1,690 g/l

	specific weight	solid content %		theor. coverage
		by weight	by volume	
B 92	1.670 ± 20 g/l	79,8	62,6	10,2 - 12,3 m ² /l

The information given in this technical data sheet is based on present scientific and technical knowledge and thus does not exempt the customer from testing the suitability of our products for their intended purposes.