

Product name: SINTOFIX 1K WHITE F 82

General Features

Synthetic alkyd primer for wood.

- Excellent sanding properties.
- Fast drying
- Excellent filling.
- Good vertical spaying features

Substrate preparation

On old painted wood, remove old paint by sanding the substrate.

On new wood with no impurity, apply one or two coats and than sand the surface with 400 grain paper.

Over-coating after 10-15 hours with matt or glossy synthetic enamels.

Recommended applications

To be used on wood applications, such as matchboarding or window frames.

Application method

- spray gun
- roller and brush

Product preparation

Thinning:

product	by weight
F 82	100
Synthetic thinner or white spirit	10 – 20

Technical and supply data

Solid content (% w/w)	min: 70,5	max: 71,5
Solid content (% v/v)	min: 56,0	max: 57,0
Specific weight (g/l)	min: 1300	max: 1400
Application Viscosity (sec – CF4)	17-20	
Theoretical coverage (g/mq))	200	

Drying time at 20°C

Dust free	10 minutes
Touch free	40 minutes
Dry to use/service	6 hours

Shelf life

12 months at + 5/35°C

The information given in this technical data sheet is based on present scientific and technical knowledge and thus do not exempt the customer to test the suitability of our products for the use and for the intended purposes.